

PermaStamp Plus® DATA SHEET

A high performance mortar **suitable to replace** traditional floorings (paving concrete, natural stones, and ceramic tiles, etc). It is formulated to be applied on an existing floors*. The mortar is to be applied and stamped from 5 to 20 mm thickness.

*For fresh concrete surfaces PermaStamp hardener to be used instead.

Composition

Product based on high resistance cement, selected aggregates, UV resistant pigments, additives and synthetic resins which give excellent workability.

Features and Applications

- Can be applied both indoors and outdoors directly on leveled concrete floors.
- Suitable for all types of walkways, residential roads, parking, shopping areas, building entrances, and heavy traffic warehouses etc.
- Suitable for restaurants floors, shops, trading centers and around swimming pools.
- Non slip. Resistant to humidity.
- Available in 10 basic colours: SILVER, BORDEUX, CHROME, CLAY, TERRACOTA, CUERO, ALBERO, IVORY, WALNUT AND PIZARRA

| Silver | Bordeux | Chrome | Clay | Terracota | Cuero | Albero | Ivory | Walnut | Pizarra |
|---|---|---|---|---|---|--|---|---|---|
|  |  |  |  |  |  |  |  |  |  |

Instructions for Use

- Make sure the area of application is clean and ready to use
- Add 3 liters of water per bag of PERMA – STAMP® Plus using a mechanical mixer.
- After mixing pour the Perma – Stamp plus mix on the floor surface and level with a steel trowel up to a maximum thickness of 20 mm
- Ensure that Perma - Stamp® plus fully covers the application areas
 - After a reasonable time, when the mortar has started hardening, dust over with Permafix Demoulding Agent to avoid the adherence of the moulds
- The moulds are set and pressed uniformly, so that the pattern is stamped in an even way
- Wait 72 hours and then clean the demoulding agent from the flooring by means of water pressure jet.

- Finish the flooring by applying PERMAFIX® Varnish.

Cautions

- Do not apply above 30°C.
- Do not apply when there is a risk of rain or strong wind.

Technical data

| | |
|-------------------|----------------------|
| Aspect | COLOURED powder |
| Density of powder | 2 g/cm ³ |
| Approximate yield | 20 kg/m ² |

Packaging

20 Kg Paper Bag.

Expiration

1 year in original packaging, sheltered from weather conditions and humidity.